

**ESTI**

7 Tall Oaks Drive  
Warren NJ 07059 USA  
Phone: 732-369-6187  
Fax: 908-349-3115

## H550

### CHARACTERISTICS

High Stiffness, Good Heat Resistance

### APPLICATIONS

General Articles

### SPECIFICATIONS

Properties	ASTM	Unit	Standard Values
MI	D1238	g/10min	11.0
Density	D792	g/cc	0.903
Tensile Strength (Yield)	D638	kg/cm <sup>2</sup>	380
Elongation (Yield)	D638	%	10
Elongation (Break)	D638	%	>500
Flexural Modulus	D790A	kg/cm <sup>2</sup> (×1,000)	16
Rockwell Hardness	D785	R scale	105
IZOD Impact Strength	D256	kg.cm/cm	2.5
Vicat Softening Point	D1525B	°C	152
Heat Distortion Temp	D648	°C	125
Mold Shrinkage (MD/TD)	D955	%	1.5~1.9
UL Rank	-	-	94HB
Haze	D1003	%	
Coefficient of Friction	D1894	-	
Young's Modulus	D882	kg/cm <sup>2</sup> (×1,000)	
Heat Sealing Temp	-	°C	

\*The listed values should be used for referential purpose only.

### PACKAGING

PVC is packed in either 20kg (44 lbs) paper bag or 500kg (1,102 lbs) super bag.

**MATERIAL SAFETY DATA**

For a current material safety data sheet (MSDS) and other technical assistance, please contact ESTI at [songyubao@estichina.com](mailto:songyubao@estichina.com) or [productinfo@estina.com](mailto:productinfo@estina.com).